

BOA-TAPE™

No primer or torch, just peel, tape and go

Boa-Tape™ is a tape system designed for sealing joints against ground water infiltration. Used to encapsulate manholes, vaults and protect pipelines.

The 50 mils elastomeric mastic in combination with 15 mils of a woven polypropylene, makes this pressure sensitive tape extra sticky.



Pressure sensitive woven polypropylene infiltration sealing tape for concrete, steel and polyethylene.


APPLICATIONS:

- » Manhole Encapsulation/Sealing
- » Pipelines
- » Repair and Rehabilitation
- » Step-Down Joints
- » Square/Rectangular Vaults
- » Septic Tanks/Vaults
- » Provides Corrosion Protection

Available in 12", 6" and 4" widths x 150ft. rolls

BOA-TAPE™ PRIMARY FEATURES AND BENEFITS INCLUDE:

- » High bonding force -
 - Accommodates ground movement
 - Seals against ground water infiltration
- » High impact and penetration resistance
 - Toughness to resist soil stress
- » Impermeable -
 - Provides corrosion protection
- » No special tools -
 - Quick and easy installation
 - No primer required
 - No touch required to adhere tape



- » Clean all exterior surfaces of the manhole with a brush or broom to remove any loose cement, dust or small rock particles.



- » Remove 8" (20cm) of release backing and position exposed tape surface on cleaned seam area. Expose 8" (20cm) of tape at a time by pulling release backing away from mastic as tape is wrapped around the entire circumference of the manhole, vault or pipe.



- » Carefully cut the Boa-Tape when applying over cast iron manhole gussets. Gently mold the tape around gussets with roller/gloved hand.

BOA-TAPE™ CONCRETE SEALING SYSTEM - TYPICAL SPECIFICATION

NOTE: For other material specifications, contact GPT.

1.0 Scope:

Apply GPT Pressure Sensitive Primerless Boa-Tape™ on exterior concrete manholes or other structures at locations indicated by the Engineer to protect manhole and mitigate infiltration/exfiltration of water and other contaminants. Boa-Tape should be applied over a dust-free, dry concrete surface. The Boa-Tape™ system should be as manufactured by GPT, Houston, Texas to ISO 9001:2008 standards.

2.0 Tape: Woven Polypropylene Membrane with Elastomeric Adhesive

The pressure applied Boa-Tape™ should consist of a 4", 6" or 12" wide wrap-around tape system 65 mils thick with a 15 mil membrane and 50 mils of integrated primer and elastomeric adhesive. Peel Strength should be a minimum of 12.5 lb./in., per ASTM D 1000. Tensile Strength should be 75 lbs/inch width. Mastic softening point should meet or exceed 240° F +/- 10 % in accordance with ASTM E-28. Water Absorption should be less than .5% per ASTM D 570.

3.0 Warranty:

All products are warranted against failure caused by manufacturing defects for a period of one year. Any product found to be so defective and returned within one year from date of shipment will be replaced without charge. The above warranty is made in lieu of, and we disclaim, any and all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose, and buyer agrees to accept the products without any such warranties. We hereby disclaim any obligation or liability for consequential damages, labor costs or any other claims or liabilities of any kind whatsoever.

BOA-TAPE™ SEALING SYSTEM PROPERTIES

ADHESIVE	ASTM TEST	TEST RESULTS
Softening Point	ASTM E-28	240° F 116° C
Dielectric Strength	ASTM D-1000	350 volts/mil
TAPE		
Tensile Strength	ASTM D-1000	75 lbs./inch width
Elongation	ASTM D-1000	40%
Puncture Resistance	ASTM E 164	200 lbs.
Water Absorption	ASTM D-570	0.05%
Penetration Resistance	ASTM G-9	PASS
Fungal Resistance	ASTM G-21	Growth-None

RISER-WRAP®



- » For extreme applications: Consider Riser-Wrap® heat shrink sleeves.
- » Riser-Wrap® used to rehab. an existing manhole submerged in runoff water.

GPT1-4_08.2016



www.gptindustries.com

4990 Iris Street
Wheat Ridge, CO 80033
Tel: (303) 988-1242
Fax: (303) 988-1922

6455 Clara Road, Suite 300
Houston, TX 77041
Tel: (713) 747-6948
Fax: (713) 747-6029

2 Woodlands Sector 1
#03-11 Woodlands Spectrum 1
Singapore 738068
Republic of Singapore

Unit 3-5, Chester Road
Colmworth Business Park
Eaton Socon, St. Neots
Cambridgeshire, PE 19 8YT

Oilfields Supply Center Ltd.
Executive Office 4, PO Box 1518
Jebel Ali Free Zone, Dubai
United Arab Emirates